

Nonlinear Optical Properties of Nanostructured Supramolecular Organic Semiconductor

JaeTae Seo¹, Qiguang Yang¹, SeongMin Ma¹, Linwood Creekmore¹, Russell Battle¹, Ashley Jackson¹, Tifney Skyles¹, Herbert Brown¹, Bagher Tabibi¹, Sam-Shajing Sun², Cheng Zhang², SungSoo Jung³, and Min Namkung⁴

¹Department of Physics, Hampton University, Hampton, VA, 23668, USA

²Chemistry Department, Norfolk State University, 700 Park Avenue, Norfolk, VA 23504, USA

³Korea Research Institute of Standards and Science, Daejeon, South Korea, 305-600

⁴Astrochemistry Branch, NASA Goddard Space Flight Center, Greenbelt, MD, 20771, USA

Email: jaetae.seo@hamptonu.edu

Abstract. Resonant third-order optical susceptibility and hyperpolarizability of donor polymer in chloroform were revealed to be $\sim 2.5 - 9.1 \times 10^{-20} \text{ m}^2/\text{V}^2$ and $\sim 8.6 \times 10^{-42} \text{ m}^5/\text{V}^2$ by degenerate four-wave mixing in nanosecond scale at 532 nm, which was attributed to the resonant enhancement.

1. Introduction

Organic materials are attractive because of their ultrafast, broad band response as well as low absorption. Conjugated organic molecules and polymers, which have large and fast optical nonlinearities due to a delocalized π electron system, have potential applications in nonlinear optical devices. The optical nonlinearities are expected to increase by substituting electron donors through the electric-induced effects and the charge transfer effects. Compounds with an intramolecular charge transfer have large optical nonlinearities due to the transfer of electron density between the donor (D) and acceptor (A). The block copolymer is a single material where donor and acceptor components are covalently linked by non π -conjugate chains. D and A are physically different from each other and therefore have the tendency to nano-phase separation. "Perfect" nano-scale morphology is achieved via judicious design of the material structure.

The third-order nonlinearities of the donor, acceptor and the corresponding block copolymer were investigated at 532 nm for photonic nonlinear applications. In this article, we reported our preliminary results on both the donor and acceptor polymer in chloroform. The results showed that the donor had much larger third-order nonlinearity than that of the acceptor because of the stronger resonant absorption at the excitation wavelength at 532 nm of the donor than that of the acceptor. The block copolymer is expected to have larger nonlinearity than that of the donor because of the possible contribution from the intramolecular charge transfer effect.

2. Molecular Structures and Linear Absorption

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 2006		2. REPORT TYPE N/A		3. DATES COVERED -	
4. TITLE AND SUBTITLE Nonlinear Optical Properties of Nanostructured Supramolecular Organic Semiconductor				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Physics, Hampton University, Hampton, VA, 23668				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited					
13. SUPPLEMENTARY NOTES THE SEVENTH INTERNATIONAL CONFERENCE ON NEW PHENOMENA IN MESOSCOPIC STRUCTURES & THE FIFTH INTERNATIONAL CONFERENCE ON SURFACES AND INTERFACES OF MESOSCOPIC DEVICES 27 November2 December 2005, Maui, Hawaii, USA					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT SAR	18. NUMBER OF PAGES 4	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

The molecular structures of the donor, acceptor, and the block copolymer were shown in figure 1. In the block copolymer case, an effective charge separation can be obtained through photoexcitation of the donor component. Thus, this kind of supramolecular system is an ideal candidate for the investigation of the charge transfer caused optical nonlinearities.




Figure 1. Structure of the donor, acceptor, and the block copolymer.

The typical linear absorption spectrum of both the donor and acceptor were shown in figure 2. At the wavelength of 532 nm, the absorption coefficient of the donor in chloroform with a weight concentration of 0.5% is about 3.7 cm^{-1} , which is 24 times larger than that of the acceptor with the same concentration. The absorption peaks of the first absorption bands are at 468 nm and 444 nm for the donor and acceptor, respectively. These absorption bands were assigned to the absorption from the ground state to the first excited state. The lifetimes of these states can be estimated by the simple time-resolved luminescent measurements.




Figure 2. Absorption spectra of the acceptor (left) and donor (right) samples. Weight concentrations of the copolymers are given in the figure.

3. Nonlinear Optical Properties

Forward degenerate four-wave mixing (DFWM) was used to measure the third-order nonlinearity. The light source was a Nd:YAG laser operated at 532 nm with 8 ns pulse width and 10 Hz repetition rate. Two laser beams with wave vectors k_1 and k_2 were focused in coincidence on the sample, whose thickness was 1 mm, at a small angle of 2° . The laser beam passed through an attenuator for intensity adjustment. The two spatially and temporally overlapped beams wrote a dynamic grating in the sample

and then the beams themselves were diffracted by the grating in directions of $2k_1-k_2$ and $2k_2-k_1$, respectively. Since beam k_1 is much stronger than beam k_2 , the signal in the $2k_1-k_2$ direction is much stronger than that in the $2k_2-k_1$. The diffracted signal in the $2k_1-k_2$ direction, which was proportional to the third-order nonlinear susceptibility $\chi^{(3)}$, was detected by a photomultiplier and boxcar averager system.

As shown in figure 3, a cubic dependence of the signals of the donor samples on the total input intensity was obtained which indicates that only third-order nonlinearity contributes to the diffracted signal. Thus, the third-order nonlinearity of the samples can be safely extracted from the degenerate four-wave mixing measurement in this intensity range.




Fig. 3. Logarithmic plot of the DFWM signal in the donor samples at 532 nm as function of total pump intensity at around zero delay. The solid line is a best fit to the data, giving an $I^{3.03-3.1}$ dependence. The weight concentrations of the samples are shown in the figure.

The third-order nonlinear optical susceptibility, $\chi^{(3)}$, of each donor sample was estimated to be $\sim 2.5 - 9.1 \times 10^{-20} \text{ m}^2/\text{V}^2$ ($\sim 1.8 - 6.5 \times 10^{-12} \text{ esu}$) from its measured intensity of the phase conjugate signal, I_s , relative to that of CS_2 under the same conditions using the following expression [1]

$$\chi_S^{(3)} = \sqrt{\frac{I_S}{I_R} \left(\frac{n_S}{n_R} \right)^2} \left(\frac{L_R}{L_S} \right) \left(\frac{\alpha L}{e^{-\alpha L/2} (1 - e^{-\alpha L})} \right) \chi_R^{(3)}, \quad (1)$$

where, I is the signal intensity of the DFWM signal beam, n is the refractive index ($n_s \sim 1.46$, $n_R \sim 1.63$ [2]), L is the sample path length ($L_s = L_R \sim 1 \text{ mm}$), α is the linear absorption coefficient at 532 nm ($\alpha = 2.3A/d \sim 3.86, 3.69, 2.44, 2.26, 1.93, 1.40 \text{ cm}^{-1}$, $d = 1 \text{ cm}$) for different concentrations of the sample, and S and R indicates sample and reference. The excellent and stable third-order optical response solvent, carbon disulfide (CS_2 , 99+ %, spectrophotometric grade, Aldrich), was selected as a reference. It has been assumed that the reference has no linear absorption at the excitation wavelength at 532 nm. The third order nonlinear susceptibility of CS_2 was reported to be $\sim 9.5 \times 10^{-21} \text{ m}^2/\text{V}^2$ ($\sim 6.8 \times 10^{-13} \text{ esu}$) in the nanosecond time-scale [3].

The third-order nonlinear susceptibility of the donor in chloroform is correlated to the donor concentration and the effect of the dielectric confinement [4]

$$\chi^{(3)} = f^4 N_a \gamma^h C \quad (SI) \quad (2)$$

where $f = (2 + n^2)/3$ is the simplified local field, n is the refractive index ($n \sim 1.46$), N_a is the Avogadro's number, and C is the concentration of donor in chloroform. The third-order nonlinear susceptibility of the donor in chloroform has a linear dependence as expected in equation (2). The hyperpolarizability (γ^h) of donor samples was extrapolated from the slope ($f^4 N_a \gamma^h$) of the third-order nonlinear susceptibility as a function of concentration plot as shown in figure 3. The hyperpolarizability of the donor sample was estimated to be $\sim 8.6 \times 10^{-42} \text{ m}^5/\text{V}^2$ ($\sim 6.0 \times 10^{-28} \text{ esu}$).




Fig. 4. Nonlinear susceptibility of the donor sample as a function of mole concentration.

The third-order nonlinearity from the acceptor polymer in chloroform was not observed, while that of the donor polymer in chloroform exhibited large third-order nonlinearity ($\sim 2.5 - 9.1 \times 10^{-20} \text{ m}^2/\text{V}^2$) at the input intensity level of $\sim 100 \text{ MW}/\text{cm}^2$, as shown in figures 3 and 4. This is mainly due to the relatively smaller linear absorption of acceptors at 532 nm for a given excitation intensity level than that of a donor polymer in chloroform. The large third-order nonlinear susceptibility of the donor polymer in chloroform is attributed to resonance enhancement. The nonlinearity of the block copolymer is expected to be even larger at the higher intensity level or ultrafast time scale because of the following reasons. First, the overall photon-induced charge-transfer (CT) efficiency reaches unity since every donor block is ensured to have interaction with an acceptor block. Second, the distance between D and A can be tuned to a certain level so that the charge recombination rate is greatly reduced, while the CT process is still significantly faster than the decay of the exciton. Third, the charge recombination is further suppressed in the D/A nanometer-level phase-separated self-assembled structure, since the strongest D-A interaction, i.e. π - π stacking between D and A, can be eliminated through judicious selection of side-chains of donor and acceptor blocks. Fourth, π -stacking of donor (acceptor) blocks produced an effect similar to that in discotic liquid crystals: greatly enhanced hole or electron mobility. Fifth, the charge collection efficiency can be optimized through realization of continuous paths for both electrons and holes in block copolymers in several types of known morphologies such as the ordered bi-continuous double diamond phase and the gyroid phase. Therefore we expect that the block copolymer is a very good candidate for nonlinear optical device application, such as nonlinear transmission limiting and optical switching.

This work at Hampton University was supported by Army Research Laboratory (DAAD17-02-C-0107), Army Research Office (DAAD19-03-1-0011, W911NF-04-1-0393), National Science Foundation (EEC-0532472, HRD-0400041, PHY0139048), and Department of Energy (DE-FG02-97ER41035).

References

- [1] R. L. Sutherland, *Handbook of Nonlinear Optics*, Marcel Dekker, Inc., 1996, page 390 ($\chi^{(3)}$), page 457-458 (refractive index).
- [2] B. Illine, K. Evain, and M. L. Guennec, "A way to compare experimental and SCRF electronic static dipole polarizability of pure liquids", *J. Mol. Struct. (Theochem)* **630**, 1 (2003).
- [3] P. Wang, H. Ming, J. Xie, W. Zhang, X. Gao, Z. Xu, and X. Wei, "Substituents effect on the nonlinear optical properties of C60 derivatives," *Opt. Comm.* **192**, 387 (2001).
- [4] B. Yu, C. Zhu, and F. Gan, "Optical Nonlinearity of Bi₂O₃ nanoparticles studied by Z-scan technique," *J. Appl. Phys.* **82**(9), 4532 (1997).